

KWA – ZULU NATAL
 T: 031 701 2619
 E: natal@mcc-sa.co.za
 Unit 7, Marlmead, 4 Reed Place,
 Maxmead, Pinetown, 3610

MULTI HYSEAL 210

Cementitious Water-Resistant Slurry

Description

MULTI HYSEAL 210 is water resistant cementitious slurry. High adhesion and water-resistant properties allow application to almost any surface. It bonds to concrete surfaces through moisture absorption, blocking the pores to resist water penetration.

Typical Applications

A slurry application for adding water resistance to sewage tanks, reservoirs and pools, shower walls and bases, balconies, pre-stressed concrete slabs.

Advantages

- Excellent adhesion
- High bond strength
- Easy application
- Water resistant
- Non-toxic

Typical Properties

Appearance	Grey
Coverage per coat	12m ² for 20Kg
Finish	Textured
Working Time	20 Minutes
Initial Set Time	30 Minutes
Hard Set Time	4 Hours
Overcoat Time	12 Hours
Application Temp.	15°C to 25 °C
Full Flex	3 Days
Application Thickness	1mm per coat
Target Thickness	3mm (3 coats)
Compressive Strength	20 MPa (28 days)
Water Required	7 Litres


Watch Points

- Surfaces need to be able to dry out
- Do not add more water to the mix once initial set occurs
- Water addition must be checked on site for placement consistency
- Allow 5 days before exposing the slurry to extended water submersion.

KWA – ZULU NATAL

T: 031 701 2619

E: natal@mcc-sa.co.za

Unit 7, Marlmead, 4 Reed Place,
Maxmead, Pinetown, 3610**MULTI CONSTRUCTION
CHEMICALS**

www.mcc-sa.co.za

MULTI HYSEAL 210

Directions for Use

Surface Preparation:

Surfaces are to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, mould oil or curing compound from concrete surfaces using wire brush, bush hammer, scabblor or other plant as appropriate. When repairing damaged concrete, ensure that all loose concrete has removed down to a firm base. Repair with MULTI PLAST 1038 or MULTI GROUT CEM 60. Surfaces can be damp but not continually wetting out or bleeding water.

Priming:

No priming is required. Dry surfaces are to be wetted with water and remain damp during application of the MULTI HYSEAL 210.

Application:

Mix 20Kg MULTI HYSEAL 210 (Powder) to 7 litres water MAXIMUM to obtain a slurry consistency. Less water can be added to obtain a thicker slurry mix. Ensure all lumps have been broken up and apply using a block brush or sprayer over surfaces. Use within 20 minutes of mixing with continuous agitation during application. DO NOT ADD MORE WATER to reconstitute the mix, rather discard the mix and make fresh. Apply with a sprayer or block brush or at a rate of 1mm thickness in one directional strokes (e.g. horizontally). Allow to cure for 12 hours between coats. Apply a second at right angles to the first one (e.g. vertically). A third coat maybe applied at right angles to the second coat (e.g. horizontally) after 12 hours where a high degree of certainly is required for waterproofing capabilities with a target thickness is 3mm. Once complete, keep exposed surfaces of the MULTI HYSEAL 210 damped down for 2-3 days using mist spray or using concrete curing compound to guard against premature dehydration of the slurry.

Equipment Care

All tools should be cleaned with water immediately after use. If delayed, equipment will need mechanical action to clean or be discarded.

Packing

Supplied in 20Kg powder.

Quality Assurance

Multi Construction Chemicals South Africa (PTY) Ltd production and testing programs comply with all local and international testing standards.

REVISION: 3.1